



Head Office: 4/125 Highbury Rd, BURWOOD VIC 3125

Installation of Z-Tile Ledgestone Cladding

Following is a method statement for the installation of Z-Tile Ledgestone cladding.

Product weight: 60-65kg M2

Fixing Height: Up to 4 metres

Substrate: Masonry Brick

Preparation

- Substrate and cladding to be clean and dust free.

Adhesive

- Kerabond Plus mixed with Isolastic 50 or Keraflex Maxi or Mapei Keraflex Maxi S1

* Adhesive to be applied to both the substrate and the back of the natural stone.

Mechanical Fixing

- Mechanical pinning to be installed at intervals of 600mm vertical.

Installation Restrictions

- No more than 1200mm in vertical height to be installed in a day

Substrate: Stone Board

Preparation

- Installation of expanded metal sheeting to the surface of the stone sheet. Fixed by screws at 150mm centres (Recommendation only).

Adhesive

- Mapei adhesive Keraflex Maxi S1

* Adhesive to be applied to both the substrate and the back of the natural stone

Additional Mechanical Fixing

- Support angle to be permanently installed under any free standing cladding stone.

I.e. - Above window openings

- Free standing entry

Note

- All work to be carried out in accordance with BCA.
- Materials used in accordance with manufacturers specifications.
- All Substrate expansion joints to be mirrored into stone work.